

TITANIUM DIOXIDE

T e c h n i c a l D a t a

CR-834

TRONOX® CR-834 rutile titanium dioxide pigment provides excellent optical properties including high brightness, tint strength and blue undertone with medium durability for a wide range of general purpose applications and resins.

Applications

Rigid and flexible PVC ■ General purpose polyolefin masterbatches ■ General purpose polystyrene and ABS injection and blow molding ■ Rubber ■ Liquid color

Typical Properties¹

TiO ₂ content %	97
Density	
Specific gravity	4.2
Bulk	0.8 kg/l or 50 lbs/cu.ft.
Oil absorption	15
pH	7.5
Specific Resistance, kohms-cm.	8
Average particle size ² (μ m).	0.17
Specification	
ASTM D-476-00 (2005)	Type II
ISO 591-1:2000	R1
NSF/ANSI Standard	14/61
FDA	Indirect food additive ³

¹Typical properties not to be construed as specifications

²By electron microscope

³Limitations apply. Contact Tronox representatives for more information.

The information herein is believed to be reliable. However, no warranty, expressed or implied, is made as to its accuracy or completeness and none is made as to the merchantability of the material or its fitness for any purpose. The manufacturer shall not be liable for consequential damages or for damages to persons or property resulting from its use. Nothing herein shall be construed as a recommendation for use in violation of any patent.

Plant Locations:

Botlek, The Netherlands
Mississippi, U.S
Kwinana, Australia

Sales Offices:

Oklahoma City 1-800-654-3911
Singapore +65-6255-0098
Shanghai, China +86-21-63912658
Perth, Australia +61-8-9361-4700
Botlek, The Netherlands +31-181-246600

TRONOX